

Product name		Product group	Production location
Talbot Blend Imperial		Y1	Erbaa/Tokat
Colour			
No description			
Format			
Moulding method		Hand form	
Specific dimensions: 225 x 105 x 68 mm		Between batches the average size and color may slightly differ.	
Essential Characteristics - EN771-1			
 NPD			
Dimensional tolerances	T2		
Range	R1		
Active Soluble Salts	S2		
Mean Compressive strength	$\geq 20 \text{ N/mm}^2$	Tested to the bed face	
Normalized Compressive strength	NPD	Tested to the bed face	
Dimensional stability	NPD		
Bond Strength general	$0,15 \text{ N/mm}^2$		
Bond Strength thin layer	$0,30 \text{ N/mm}^2$		
Reaction to fire	A1	Category	
Water absorption	$\leq 15\% \text{ m/md}$		
Water vapour permeability	5/10		
Net dry density	$1610 \text{ kg/m}^3 \text{ (D1)}$		
Gross dry density	$1720 \text{ kg/m}^3 \text{ (D1)}$		
Thermal conductivity Lambda 50/50	$\leq 0,41 \text{ W/m.K}$		
Durability against freeze thaw	F2		
Dangerous substances	NPD	According to Annex ZA 3	
Other Characteristics			
Initial rate of water absorption - Non-coated Bricks	$1,5 - 4.0 \text{ kg/m}^2 \cdot \text{min (IW3)}$	Value according EN771-1:2011 - 5.3.8	
Initial rate of water absorption - Coated bricks	NPD	Value according EN771-1:2011 - 5.3.8	
Freeze/thaw resistance	NPD	B 27-009	
Thermal conductivity Lambda 90/90	NPD		
Thermal conductivity Lambda Ui	NPD		
Thermal conductivity Lambda Ue	NPD		
			
Storage & handling		Cutting	
<ul style="list-style-type: none"> - Store packs on a clean surface and cover them - Process from multiple packs at the same time - Follow the Vandersanden processing guidelines 		Cutting with power tools may generate dust. This dust may contain silica or quartz particulate which may constitute a hazard. Persons undertaking work of this nature are advised to wear dust masks (FFP3).	
*All our Coated bricks are only coated on the facing sides. Coated products are specially labeled and recognisable with a "C" logo on the top left-hand side of the packaging. Always check if using coated or non-coated bricks. Match the mortar to the specified initial water absorption.			